PRODUCT SELECTOR GUIDE								
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS
FUNC	TIONAL ADDITIV	ES						
A6220	A-284	93158-39-5 (Y)	Dibutyl-1,4 Cyclohexanedicarboxylate	H <sub>3</sub> C 0 0 CH <sub>3</sub>	<ul><li>Plasticizer</li><li>Non-phthalate</li><li>Very low viscosity</li></ul>	Colorless Liquid	30	• For use as a plasticizer in applications where human contact is expected
R1231	A-304	70293-55-9 (N)	4-Metacryloxyethyl Trimellite Anhydride	$H_3C$ $H_2$ $O$	<ul><li>Adhesion Promoter</li><li>Versatile adhesion promoter</li></ul>	White Powder/Crystals	N/A	Adhesion promoter
R1251	A-675-100%	148019-46-9 (Y)	PMGDM	$\begin{array}{c} \begin{array}{c} & & & \\ & & & \\ & & & \\ & & & \\ H_{2}C \\ & & \\ CH_{2} \end{array} \begin{array}{c} \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	Versatile adhesion promoter	Light Yellow	Very viscous	Adhesion promoter
R1217-M	A-478-M	Not assigned (N)	Pyromellitic Dianhydride Dimethacrylate – Mixture of Isomers	$\begin{array}{c} & & & \\ & & & \\ H_{2}C \\ H_{2}C \\ H_{2} \\ H_{3}C \\$	Versatile adhesion promoter	Fine White Powder	N/A	Adhesion promoter
A6165	A-6165	1151654-51-1 (Y)	Soluble additive that on addition to a conductive adhesive formulation can significantly decrease the volume resistivity of the cured material	Unavailable	<ul> <li>Improves electrical conductivity in metal filed conductive paste formulations</li> <li>Soluble in most resin systems</li> <li>May improve thermal conductivity in some formulations</li> </ul>	Dark Brown Viscous Liquid	**	<ul> <li>Increases electrical conductivity of resin system</li> </ul>

Desig	gner Dlecules Inc.		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
FUNCTIONAL ADDITIVES continued										
A6225	A-6225	No (N)	Antibleed Additive – Silicone Mercapto Propionate (SMP)	Unavailable	<ul> <li>Excellent bleed control</li> <li>Co-curable in most systems</li> <li>Minimal adhesion degradation</li> <li>Non-halogenated – a 'green' alternative to conventional anti-bleed and mold release materials</li> </ul>	Colorless Liquid	50	<ul> <li>For use as an additive to reduce resin bleed out specifically on metal surfaces</li> </ul>		
IMIDE-	EXTENDED BISI	MALEIMIDES								
R1155	BMI-689	682800-79-9 (Y- LVE)	A unique very low viscosity BMI resin	H <sub>2</sub> C H <sub>3</sub> C H <sub>3</sub> C Contains unsaturation	<ul> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> </ul>	Yellow to Amber Liquid	1,500 ± 500	Base resin or additive in thermoset formulations designed for high temperature resistance		
R1232	BMI-1400	1224691-98-8 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates	$ \left\{ \left( \begin{array}{c} & & & \\ & & \\ & & \\ & & \\ & \\ & \\ & \\ $	<ul> <li>Specialty formulated lower viscosity version of BMI-1700</li> </ul>	Amber	6,500 ± 1,000 (60°C)	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		
R1203	BMI-1500	1290041-56-3 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates		<ul> <li>Soluble in many reactive diluents</li> <li>Hydrophobic</li> <li>Superior thermal stability</li> <li>High adhesion to various substrates</li> </ul>	Amber Viscous Liquid	20,000 ± 10,000 (60°C)	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		

Desi	gner Dlecules Inc.		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
IMIDE-	IMIDE-EXTENDED BISMALEIMIDES continued									
R1191	BMI-1700	1224691-98-8 (Y)	An amorphous, low molecular weight bismaleimide oligomer that exhibits good adhesion to a variety of substrates	$ \begin{cases} \begin{pmatrix} \cdot & \cdot & \cdot \\ \cdot & \cdot & \cdot & \cdot \\ \cdot & \cdot &$	<ul> <li>Soluble in many reactive diluents</li> <li>Hydrophobic</li> <li>Superior thermal stability</li> <li>High adhesion to various substrates</li> </ul>	Amber High Viscous Liquid	30,000 ± 10,000 (60°C)	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		
R1316	BMI-2500	(Y)	Designed to extend the range of applications suitable for use with Designer Molecules, Inc. Imide- Extended Bismaleimide Oligmers to those in need of higher Tg and modulus.	N/A	<ul> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> <li>Low pH hydrolytic resistance</li> <li>Reduce resin bleed out</li> </ul>	Light Yellow Glassy Powder	N/A	<ul> <li>Additive to increase flexibility, hydrophobicity, thixotrophy</li> <li>Base resin – produces films that are tough, flexible, and have good peel strength</li> </ul>		
R1090	BMI-3000 Gel	921213-77-6 (Y)	Bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides.	Where n = 1 to 10	<ul> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> </ul>	Red-Amber Gel	N/A	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		
R1225	BMI-3000 CG	921213-77-6 (Y)	Low cost bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides.	Where n = 1 to 10	<ul> <li>Low cost</li> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> </ul>	Light Yellow Powder	N/A	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		

Desid	gner Dlecules Inc.		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
IMIDE-	IMIDE-EXTENDED BISMALEIMIDES continued									
R1130	BMI-3000 Powder	921213-77-6 (Y)	Bismaleimide oligomer that exhibits excellent flexibility and, on cure, forms very tough hydrophobic polyimides	$\begin{cases} \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	<ul> <li>Toughener</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Superior thermal stability</li> </ul>	Light Yellow Powder	N/A	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> <li>Adhesion to metal</li> </ul>		
R1171-P	BMI-5000 Powder	921213-77-6 (Y)	Imide-extended bismaleimide oligomer that exhibits excellent toughness in the cured state with intermediate cross-link density.	$\begin{cases} \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	<ul> <li>Low cross-link density</li> <li>Non-tacky</li> <li>Film-forming</li> <li>Maleimide functional oligomer</li> <li>Cures to a tough thermoset</li> <li>Additive to enhance toughness in thermoset compositions</li> </ul>	Light Yellow Powder	N/A	<ul> <li>Film adhesives</li> <li>Thermally resistant adhesives</li> </ul>		
R1171-T	BMI-5000 Toluene	921213-77-6 (Y)	Imide-extended bismaleimide oligomer that exhibits excellent toughness in the cured state with intermediate cross-link density.	$\begin{cases} \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	<ul> <li>Low cross-link density</li> <li>Non-tacky</li> <li>Film-forming</li> <li>Maleimide functional oligomer</li> <li>Cures to a tough thermoset</li> <li>Additive to enhance toughness in thermoset compositions</li> </ul>	Dark Brown Liquid	1,000	<ul> <li>Film adhesives</li> <li>Thermally resistant adhesives</li> </ul>		
R1334	BMI-6000	(Y)	A curable, low DK and Df alternative to replace both the Kapton and adhesive layers in the manufacture of FCCL materials. It can be processed in a resin system as a solid or dissolved in a solvent.	N/A	<ul> <li>Toughener</li> <li>Hydrophobic</li> <li>Super thermal stability</li> <li>Good dielectric properties</li> <li>Excellent workability</li> <li>High Tg</li> <li>Low CTE</li> </ul>	Light yellow powder	N/A	<ul> <li>Adhesive layer when laminating FCCL applications</li> <li>Adhesion promoter</li> </ul>		

Desig	gner Dlecules Inc.		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
CYCLO	CYCLOSILOXANE EPOXY HYBRIDS									
R1163	CS-697	257284-60-9 (Y)	A polyglycidyl ether cyclosiloxane monomer NOT AVAILABLE IN JAPAN	C CH3 H3C CH3 CH3 CH3 CH3 CH3 CH3 CH3 CH3	<ul> <li>Multifunctional</li> <li>UV curable</li> <li>Low chloride</li> <li>Low viscosity</li> <li>Colorless</li> </ul>	Colorless Liquid	200	UV curable additive		
R1116	CS-783	921214-21-3 (Y)	Methacrylate epoxy functional hybrid cyclosiloxane monomer	Ho Ho Ho Ho	<ul> <li>Dual cure mechanism</li> <li>Multifunctional</li> <li>UV Curable</li> <li>Low chloride</li> <li>Low viscosity</li> </ul>	Yellow Liquid	250	<ul> <li>Hybrid cures</li> <li>UV cures</li> <li>B-stageable adhesives</li> </ul>		

Designer Molecules Inc.				PRODUCT SEI	PRODUCT SELECTOR GUIDE				
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS	

PHEN	L ESTER EPOX	Y CURATIVES						
R1146	EC-234	926305-16-0 (Y-LVE)	Phenyl ester epoxy curative hybrid	O CH <sub>3</sub> O CH <sub>2</sub> CH <sub>2</sub>	<ul><li>Hybrid cure</li><li>Low viscosity</li></ul>	Light Yellow Liquid	40	<ul> <li>UV adhesives</li> <li>B-stageable adhesives</li> </ul>
R1170	EC-298	1044794-71-7 (Y-LVE)	Difunctional phenyl ester epoxy curative	H <sub>3</sub> C O CH <sub>3</sub>	<ul> <li>Stable</li> <li>Low viscosity</li> <li>Does not impede free radical cure</li> </ul>	Light Yellow Liquid	500	<ul> <li>Thermoset adhesives</li> <li>Curative for epoxy/(meth) acrylate hybrids</li> <li>Hybrid epoxy/free radical thermosets</li> </ul>
R1227	EC-312	10192-62-8 (Y)	Difunctional phenyl ester epoxy curative	$O = \underbrace{CH_3}_{CH_3} \underbrace{CH_3}_{CH_3} \underbrace{CH_3}_{O} O = O$	<ul> <li>Low cost</li> <li>Low melting point</li> <li>Thermal stability</li> <li>Hydrophobic</li> <li>Does not impede free radical cure</li> </ul>	Fine White Powder	N/A	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> </ul>
R1147	EC-326	N/A (Y-LVE)	Bisphenol A based acetate/proprionate epoxy curative	$H_3C$ $O$ $CH_3$ $H_3C$ $O$ $H_3C$ $O$ $H_3C$ $O$ $H_3C$ $O$ $H_3C$	<ul> <li>Hydrolytically resistant</li> <li>Low melting point</li> <li>Thermal stability</li> <li>Hydrophobic</li> <li>Toughener</li> <li>Does not impede free radical cure</li> </ul>	White/Yellow Solid	2,000 ***	<ul> <li>Film adhesives</li> <li>Pre-applied adhesives</li> </ul>
R1148	EC-392	107466-61-9 (Y)	Phenyl ester epoxy curative hybrid of diallyl bisphenol A	$O = \begin{pmatrix} CH_3 \\ O = \\ O = \\ O = \\ H_2C \end{pmatrix} \begin{pmatrix} CH_3 \\ CH_3 \\ H_3C \end{pmatrix} = O$	<ul> <li>Dual cure mechanism</li> <li>High cross-link density</li> <li>Multifunctional</li> <li>Thermal stability</li> </ul>	Amber Liquid	2,500	<ul> <li>B-stageable adhesives</li> <li>Epoxy and BMI co- curative</li> </ul>

Desi	gner Dlecules Inc.		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
PHEN	PHENYL ESTER EPOXY CURATIVES continued									
R1165	EC-861	1071523-12-0 (Y)	Phenyl acetate epoxy curative	HCC C C C C C C C C C C C C C C C C C C	<ul> <li>Low modulus</li> <li>Toughener</li> <li>Hydrolytically resistant thermosets</li> <li>Hydrophobic</li> <li>Thermal stability</li> <li>Does not impede free radical cure</li> </ul>	Amber/Yellow Liquid	2,500	Low stress epoxy thermosets		
R1149	EC-1074	926657-64-9 (Y)	A tetra-phenol epoxy curative derived from dimerdiol	Hoch of the form	<ul> <li>Low modulus</li> <li>Toughener</li> <li>Hydrolytically resistant thermosets</li> <li>Hydrophobic</li> <li>Thermal stability</li> </ul>	Amber Glassy Solid	N/A	<ul> <li>Film Adhesives</li> <li>Pre-applied adhesive compositions</li> </ul>		
LATENT EPOXY CATALYSTS										
R1198 R1207 R1208 R1209	ECAT Series ECAT-243 ECAT-259 ECAT-353 ECAT-434	1253404-90-8 (Y)	Imidazole Epoxy Catalysts	Unavailable	<ul> <li>Good solubility in most epoxy monomers</li> <li>Excellent latency characteristics</li> <li>Can be used as a catalyst or curative</li> <li>Turnable cures</li> <li>Promotes clean, rapid monomodal cures</li> </ul>	Refer to TDS	N/A	<ul> <li>Electronic mold compounds</li> <li>Underfills</li> </ul>		

DESIGNER MOLECULES INC.				PRODUCT SEI	PRODUCT SELECTOR GUIDE			
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS

ΜΟΝΟ	FUNCTIONAL M	ONOMERS						
R1173	MM-204	33791-58-1 (Y)	Monofunctional acrylate monomer		<ul> <li>Low viscosity</li> <li>High glass transition temperature</li> <li>Low cure shrinkage</li> <li>Hydrolytically resistant</li> <li>Diluent for thermoset resins</li> <li>High Tg</li> </ul>	Light Tan Liquid	50	<ul> <li>UV or peroxide cured resins, coatings, or adhesives</li> </ul>
R1175	MM-211	55750-53-3 (Y)	An intermediate chain length, maleimide terminated carboxylic acid	О ОН	<ul> <li>Flexible aliphatic backbone</li> <li>Maleimide and carboxylic acid functional groups</li> <li>Adhesion promoter</li> </ul>	White/Light Yellow Powder	N/A	<ul> <li>Intermediate for ester and amide linked maleimide monomers</li> </ul>
R1139	MM-220	93962-84-6 (Y-LVE)	Tricyclodecane Acrylate		<ul> <li>Low weight loss on cure</li> <li>Helps reduce cure shrinkage</li> <li>Low viscosity</li> </ul>	Light Yellow Liquid	< 100	UV cure coatings
R1121	MM-281	57079-01-3 (Y-LVE)	Maleimidoundecanoic Acid (MUDA)	О ПОЛИКИ СТАН	<ul> <li>Flexible aliphatic backbone</li> <li>Malemide and carboxylic acid functional groups</li> <li>Adhesion promoter</li> </ul>	White to Off-white Powder	N/A	Intermediate for ester and amide linked maleimide monomers
R1134	MM-290	903876-45-9 (Y)	Isobornyl Cyclohexyl Acrylate	H <sub>3</sub> C H <sub>3</sub> C H <sub>3</sub> C CH <sub>2</sub>	<ul> <li>Lower weight loss on cure than Isobornyl Acrylate (IBOA)</li> <li>Mild, pleasant odor</li> <li>Hydrolytic resistance</li> </ul>	Light Tan Liquid	250	<ul> <li>UV or peroxide cured resins, coatings, or adhesives</li> </ul>

Desic	sner Diecules Inc.			PRODUCT SEI	LECTOR GUIDE					
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
MONO	MONOFUNCTIONAL MONOMERS continued									
R1197	MM-304	N/A (N)	Isobornyl Cyclohexyl Methacrylate	$H_3C$ $H_3C$ $H_3C$ $H_3C$ $CH_2$	<ul> <li>Very low color</li> <li>Lower weight loss on cure than Isobornyl Methacrylate (IBOMA)</li> <li>Mild, pleasant odor</li> <li>Hydrolytic resistance</li> </ul>	Colorless Liquid	80	<ul><li>Dental</li><li>Reactive diluent</li></ul>		
POLYESTER ACRYLATE METHACRYLATES										
R1096	PEAM-645	921213-39-0 (Y)	Polyester acrylate/methacrylate	$H_{G_{H_{n}}} = \int_{G_{H_{n}}} \left( \int_{G_{H_{n}}} \int_{G_{H_{$	<ul> <li>High Tg</li> <li>High modulus</li> <li>Low CTE</li> <li>High adhesion I</li> <li>Thermal stability</li> </ul>	Amber Liquid	6,500	Low CTE thermosets		
R1111	PEAM-1044	921214-61-1 (Y)	Polyester acrylate/methacrylate	where $n = 1$ to 5	<ul> <li>Low warpage</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>Thermal stability</li> </ul>	Amber Liquid	(40°C)	Low stress coatings		
R1144	PEAM-1769	921214-61-1 (Y)	Polyester acrylate/methacrylate	$ \begin{array}{c} \begin{array}{c} & & \\ & & \\ & & \\ & \\ & \\ & \\ & \\ & \\ $	<ul> <li>Ultra-low modulus</li> <li>Hydrophobic</li> <li>High adhesion *</li> <li>High thermal stability</li> <li>Adhesion to metals</li> <li>Flexibilizer</li> </ul>	Amber Liquid	4,500	Low stress coatings		
Designer M	olecules, Inc. 10080 \	Villow Creek Rd., S	an Diego, CA 92131	www.designermoleculesinc.com	Tel. +1-858-348-112	2, Fax. +1-858-348-	1123 <b>Re</b> v	<b>v P</b> Page 9 of 12		

	gner Dlecules Inc.			PRODUCT SEI	PRODUCT SELECTOR GUIDE				
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS	

POLYESTER METHACRYLATES									
R1188	PEM-665	N/A (N)	Methacrylate terminated polyester oligomer	$\overset{H_{2}C_{2}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{\overset{OH_{3}}{&$	<ul> <li>Low color</li> <li>Low cure shrinkage</li> <li>Thermal stability</li> <li>Tough</li> </ul>	Light Yellow Tint Liquid	6,500 (50°C)	• Dental	
R1157	PEM-1066	951244-55-6 (Y-LVE)	Polyester methacrylate		<ul> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>High adhesion *</li> <li>Adhesion to metals</li> <li>Ultra-low warpage</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	20,000	<ul> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>	

Desi	gner Dlecules Inc.	PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS	
FUNCTIONAL URETHANES									
R1216	U-347	1371570-15-8 (N)	Phenyl glycerol urethane dimethacrylate (PGDMA)	$H_3C$ $O$ $H_2C$ $O$ $H_2C$ $CH_3$	<ul> <li>Low cure shrinkage</li> <li>Colorless</li> <li>Good refractive index</li> <li>Not bisphenol A based</li> </ul>	Clear Colorless Liquid	9,500	<ul> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>	
R1230	U-483	Not assigned (N)	IPDI urethane dimethacrylate	$H_{2}C + I_{3}C + I_{4}C + I$	<ul> <li>Low viscosity</li> <li>Low cure shrinkage</li> <li>Colorless</li> <li>Not bisphenol A based</li> </ul>	Clear Colorless Liquid	5,000	<ul> <li>Dental</li> <li>Moisture resistant coatings</li> <li>Light cure coatings</li> </ul>	
R1095	U-793	869488-57-3 920758-62-9 902742-80-9 (Y)	Urethane resin functionalized with a methacrylate and an epoxy	Unavailable	<ul> <li>Low color</li> <li>Low cure shrinkage</li> <li>Thermal stability</li> <li>Tough</li> </ul>	Light Yellow Tint Liquid	6,500 (50°C)	Dental	
R1102	U-835	869488-57-3 1003557-45-6 1003612-76-7 (Y-LVE)	Urethane resin functionalized with acrylate and methacrylate end groups	Unavailable	<ul> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>High adhesion *</li> <li>Adhesion to metals</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	20,000	<ul> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>	
R1238	U-847	86499-57-3 (N)	DDI urethane dimethacrylate monomer		<ul> <li>Low modulus</li> <li>Low color</li> <li>Low cure shrinkage</li> <li>Hydrophobic</li> <li>Flexibilizer</li> </ul>	Light Yellow Liquid	2,500	<ul> <li>Dental</li> <li>Moisture resistant coatings</li> </ul>	

Desi	gner Dlecules Inc,		PRODUCT SELECTOR GUIDE							
P/N	PRODUCT	CAS / TSCA Listed (Y/N)	DESCRIPTION	STRUCTURE **	FEATURES	APPEARANCE	VISCOSITY (25°C)	SUGGESTED APPLICATIONS		
FUNCT	FIONAL URETH	ANES continue	ed							
R1228	U-471	72869-86-4 (Y)	TMDI urethane dimethacrylate monomer	$\begin{array}{c} \mu_{ij} \mathcal{C}^{\mu_{ij}} \\ \mu_{ij} \mathcal{C}^{\mu_$	<ul><li>Low color</li><li>Low cure shrinkage</li></ul>	Slight Yellow Liquid	8,000	• Dental		
R1266	U-443	TBD (N)	TMDI urethane diacrylate monomer	$\begin{array}{c} H_{2} \subset & \int_{-\infty}^{\infty} O_{1} \int_{-\infty}^{0} H_{2} \int_{-\infty}^{0} O_{1} \int_{-\infty}$	Excellent Curing Properties	Clear, Colorless, Oil	5,500	<ul> <li>Light-cured coating resins</li> </ul>		
FORM	ULATED PRODU	JCTS								
R1267	DMI-2550	Mixture (Y)	A BMI-based coating for dispense applications	Mixture	Low modulus     Hydrophobic     Excellent hydrolytic resistance     Low stress     Adhesion to metals     Flexibilizer	Yellow to Dark Amber Liquid	700 ± 100	Die top coating applications		

R1267	DMI-2550	Mixture (Y)	A BMI-based coating for dispense applications	Mixture	<ul> <li>Low modulus</li> <li>Hydrophobic</li> <li>Excellent hydrolytic resistance</li> <li>Low stress</li> <li>Adhesion to metals</li> <li>Flexibilizer</li> </ul>	Yellow to Dark Amber Liquid	700 ± 100	<ul> <li>Die top coating applications</li> </ul>		
R1303	DMI-3006	Mixture (Y)	Modified polymide based negative type photoresist	Mixture	<ul> <li>Low modulus</li> <li>Very high electrical reliability</li> <li>UV cured-low thermal req'rmts</li> <li>Low cure shrinkage</li> <li>High heat resistance</li> <li>Good electrical properties</li> </ul>	Amber liquid	250	Wafer buffer coating		
	ALL DATA PROVIDED FOR REFERENCE ONLY AND MAY VARY BY TEST METHOD									
* \	* Various substrates ** Many of the structures are an idealized representation of a statistical distribution									
***	*** Supercooled **** Storage at < 25°C will result in precipitation of some solids. The fully liquid state can be regenerated by warming to 40°C until all solids dissolve									
LVE I	LVE Material manufactured under Low Volume Exemption (LVE) in compliance with Section 5(h)(4) of the Toxic Substances Control Act (TSCA), 15 U.S.C.									
	TO PLACE AN ORDER, REQUEST SAMPLES, OR TO SPEAK WITH US ABOUT DEVELOPING A PRODUCT FOR YOUR CHEMICAL NEEDS, CONTACT US AT 858-348-1122.									